

MRD LW CAST

APPLICATION(S) - Sanitaryware

CHEMICAL ANALYSIS (%)	Min.	Value	Max.
SiO ₂		48.3	
Al ₂ O ₃		36.0	
Fe ₂ O ₃		1.10	
TiO ₂		0.05	
CaO		0.01	
MgO		0.01	
K ₂ O		2.3	
Na ₂ O		0.01	
LOI	11.8		13.2

RESIDUE – WET sieve (mass %)

> 45 µm			3.0
---------	--	--	-----

PARTICLE SIZE ANALYSIS–Sedigraph (cumulative mass %)

< 10 µm		73	
< 5 µm		48	
< 2 µm		26	
< 1 µm		18	

PHYSICAL PROPERTIES

Moisture content (%)	15		20
----------------------	----	--	----

Casting Data

Deflocculant demand (wt%)	0.20		0.40
Cast rate (mm.)	13.0		15.3

FIRED PROPERTIES

	1250°C		
L*		92.0	
a*		1.04	
b*		6.18	
Contraction (%)		7.0	
Water absorption (%)		18.0	

PRODUCT FORM & STANDARD PACKAGING

Lump, Noodle			
1000 kg.Big bag, 50 kg bags, bulk			

QRS 042 May 2021

© Imerys Ceramics 2020

Third Edition

This version supersedes

The version dated June 2020

Sales Office

Imerys Ceramics Thailand
228 Vibhavadi Rangsit Road,
Din Dang, Bangkok, Thailand
Tel. +66 269 50 999
Fax: +66 269 50 901
www.imerys-ceramics.com

Max, Min values are specified properties.
All other values are typical. The data quoted are determined by the use of Imerys Standard Test Methods, copies of which will be supplied on request. Every precaution is taken in production to ensure the products conform to our published data. Since the products are based on naturally occurring materials, we reserve the right to change these data should it become necessary. Sales are in accordance with our "Conditions of Sales" copies of which will be supplied on request.